

PRIMER PC H+ 107

High range water reducing / super plasticizing admixture

CYS EN934-2:2009+A1:2012 (Table 3.1 & 3.2)

Product Description

PRIMER PC H+ 107 is high range Super plasticizer admixture with a unique formulation designed specifically for the use with hydraulic binders.

PRIMER PC H+ 107 has a strong dispersant action with the finer elements of concrete. This formulation enables **PRIMER PC H+ 107** to enhance the concrete workability and its mechanical strength properties. **PRIMER PC H+ 107** does not contain intentionally added chlorides and will not initiate or contribute to corrosion on steel reinforcement present in the concrete.



Dosage

- Optimum dosage of **PRIMER PC H+ 107** should be determined in trial mixes
- As a guide, the following dosages are recommended as a starting point for any trial:
In normal concrete, a dosage of between 0.25 - 2 % by weight of cement

Package

1000 lt.

Product Advantages

- Optimizes cement utilization
- High density and impermeable concrete through very high-water reduction.
- Substantial improvement in workability without increase of w/c ratio
- Minimizes segregation and bleeding problems by improving cohesion.
- Improved durability
- Improves shrinkage and creep behaviors
- Workability retention
- Improved resistance to wear and abrasion
- Lower pumping pressure
- High early and long term strengths

Overdosing

If accidental overdosing occurs it can lead to:

- Increase in workability
- Initial and final set retarding
- Segregation

For any Further Technical Information including SDS, CE LABELS and CERTIFICATES OF CONFORMITY don't hesitate to contact our QA/QC Department.
We remain at your disposal.

E-MAIL: lab@primeracm.com | Ph.+35725336671

Setting Time

The setting time is dependent on the dosage of **PRIMER PC H+ 107**, the following factors should be considered:

- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation level than ordinary cement.
- Using more than one type of admixture in the same concrete mix could affect the setting time.

Technical Data

Density	1.07 ± 0.02
Chloride content	Chloride free
PH	7 ± 2
Freezing Point	0 °C
Recommended Dosage	0.25 - 2 % by weight of cement

Product Data

Composition	Modified Synthetic polymers
Appearance	Amaranth
Storage condition	Store in a dry area between 5°C and 35°C. Protect from direct sunlight.
Shelf Life	12 months minimum from production date if stored properly in original unopened packaging.

Safety Instructions

The product may cause skin irritation. Wear gloves and goggles and apply barrier cream to your hands. In contact with eyes or mucous membrane, rinse immediately with plenty of warm water and seek medical attention without delay.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

The user of the product must test the product's suitability for the intended application and purpose. Primer Cy LTD reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations.