

Spatula Coarse Plaster (GP)

Complies with EN 998-1 (System 4) for exterior and interior use

Grain Size: 1.5 – 3.0 mm (coarse aggregate)

Clause 3.1.5.1 general purpose rendering/plastering mortar

Clause 3.1.1 rendering/plastering mortar

Clause 3.1.3.1 designed rendering/plastering mortar

Clause 3.1.4.2.1 pre-batched rendering/plastering mortar

Clause 3.1.6.5 - UNDER COAT



Product Description

Spatula Coarse Plaster is a coarse-textured, decorative plaster classified under EN 998-1 (System 4: Exterior and interior plaster with enhanced mechanical strength and weather resistance). It is designed for both manual (spatula/trowel) application and provides a durable, textured finish.

Technical Data (EN 998-1 System 4 Parameters)

Property	Test Standard	Requirement (System 4)	
Compressive Strength	EN 1015-11	≥ 6 MPa	CS IV
Adhesive Strength	EN 1015-12	≥ 1 MPa	
Capillary Water Absorption (W ₀)	EN 1015-18	≤ 0.5 kg/m ² ·h ^{0.5}	Wc1
Frost Resistance	EN 998-1	F2 (Severe frost)	
Reaction to fire	EN 13501-1	Class A1	
Fresh Bulk Density	EN 1015-6	1700 kg/m ³	
Dry Bulk Density	EN 1015-10	1280 kg/m ³	



PRIMER

ADMIXTURE AND CONSTRUCTION MATERIAL



**Building
Materials**

Safety & Storage

Shelf Life: 12 months (unopened, dry storage).

Safety Data Sheet (SDS)

Complies with EC No. 1907/2006 (REACH).

Personal Protection

Use gloves, goggles, and dust masks during handling.

Recommended Use Cases

**Exterior façades (high mechanical stress, frost exposure).
Interior feature walls (textured decorative finishes).
Repair & restoration of old mineral substrates.**

Application Guidelines

Substrate Requirements

- Must be stable, clean, and load-bearing (concrete, masonry, or cement-based renders).
- Pre-treatment with primer (e.g., acrylic-based) for porous substrates.

Mixing

- Water-to-powder ratio: ~ 25-30% (follow manufacturer's instructions).
- Mix mechanically for 3-5 minutes until homogeneous.
- Coverage: 1.5-2.5kg/m³ (2mm thickness).

Application

- Apply in one layer (2-5 mm thickness) using a stainless steel spatula/trowel.
- Texture can be adjusted (spatula strokes, circular motion, etc.).
- Open time: ~ 30-60 minutes (workability period).

Curing & Protection

- Drying time: Touch-dry in 4-6 hours, full cure in 24-48 hours.
- Protect from rain, frost, and direct sunlight during curing.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

The user of the product must test the product's suitability for the intended application and purpose. Primer Cy LTD reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations.

For any Further Technical Information including SDS, CE labels and Certificates of conformity don't hesitate to contact our QA/QC Department.
We remain at your disposal.

E-MAIL: lab@primeracm.com | Ph.+35725336671

